

TECHNICAL DATA SHEET

BARRICADE™ Concrete Repair Crack Prep Surface Paste | Revision Date 27/6/2022

2311 Royal Windsor Drive
Mississauga, ON L5J 1K5
P: 1-855-872-3996
E: help@barricadesubfloor.com

01

1. DESCRIPTION

BARRICADE™ Concrete Repair Crack Prep Surface Paste is a two-component, 100% solids, moisture-insensitive, high strength, high modulus, multi-purpose liquid epoxy gel adhesive. It meets the current ASTM C881 and AASHTO M235 Types I, II, IV & V Grade 3, Classes B & C specifications. It has passed 4 million cycles of simulated seismic tension test.

2. WHERE TO USE

Use BARRICADE™ Concrete Repair Crack Prep Surface Paste as an adhesive for setting/bonding subsurface or external reinforcements to concrete masonry or other substrates. It can also be used for reinforcing steel dowels, threaded rods, bolts, and inserts into existing concrete. Use as a multipurpose bond adhesive for structural bonding fresh or hardened concrete to hardened concrete, sealing cracks, setting Rhino injection ports prior to injection grouting, and as a pick-proof sealant.

3. ADVANTAGES

- Moisture tolerant
- High strength, high modulus structural adhesive
- Convenient 1:1 mix ratio by volume
- Rapid cure formula
- Agency Independent testing lab certification
- Solvent free
- No-sag gel consistency

4. SHELF LIFE / STORAGE

24 month shelf life when stored in unopened containers in dry conditions and stored at 40°F-95°F (4°C-35°C)

5. TECHNICAL DATA BARRICADE™ Concrete Repair Crack Prep Surface Paste

| BARRICADE™ Concrete Repair Crack Prep Surface Paste | |
|---|---|
| Storage Conditions: | 40°F – 95°F (4°C – 35°C). |
| Condition material to: | 65°F – 85°F (18°C – 29°C) before using. |
| Mix Ratio | 1:1 by volume |
| Viscosity | ¼ inch no-sag gel |
| Gel Time (60 g mass) | 10 minutes |
| Tack Free Time (73°F or 23°C) | 2 to 3 hours |
| Tensile Properties (ASTM D638), 7 day cure | |
| Tensile Strength: | 7,500 psi (51.7 MPa) |
| Tensile Elongation: | 1.2% |
| Bond Strength (ASTM C882) | |
| 1 day cure: | 2,000 psi (13.8 MPa) |
| 7 day cure: | 2,500 psi (17.2 MPa) |
| Compressive Properties (ASTM D695), 7 day cure | |
| Compressive Strength: | 12,500 psi (86.2 MPa) |
| Compressive Modulus: | 300,000 psi (2,070 MPa) |
| Shear Strength (ASTM D732) | 2,800 psi (19.3 MPa) |
| Shrinkage on Cure (ASTM D2566) | 0.001 |
| Thermal Compatibility (ASTM C884) | Pass |
| Heat Deflection Temperature (ASTM D648) | 140°F (60°C) |
| Water Absorption (ASTM D570) | 0.1% (24 hr) |

*NOTE: Epoxy cure is affected by temperature. Low temperatures will increase cure time, higher temperatures with decrease cure time.

6. CONDITION PRODUCT

Condition cartridge and contents to a temperature of 65°F to 95°F (18°C - 35°C) for easier dispensing.

7. LIMITATIONS & WARNINGS

Minimum substrate temperature is 40°F (5°C). Do not thin. Solvents will prevent proper cure.

8. MANUFACTURER'S PRINTED INSTALLATION INSTRUCTIONS

For complete installation instructions on various applications using BARRICADE™ Concrete Repair High Strength Anchoring Epoxy Paste visit www.barricadesubfloor.com or call Barricade for more information at 1-855-872-3996.



1-855-872-3996 | WWW.BARRICADESUBFLOOR.COM

© BARRICADE® All Rights Reserved

© AGT Products (IP) Inc. All rights reserved BARRICADE™ is a trademark of AGT Products (IP) Inc. Used under license by AGT Products Inc. and AGT Products (USA) Inc.

TECHNICAL DATA SHEET

BARRICADE™ Concrete Repair Crack Prep Surface Paste | Revision Date 27/6/2022

2311 Royal Windsor Drive
Mississauga, ON L5J 1K5
P: 1-855-872-3996
E: help@barricadesubfloor.com

02

9. SURFACE PREPARATION

BARRICADE™ Concrete Repair Crack Prep Surface Paste is an ideal bonding agent for multiple surfaces including concrete, brick, stone, block, and metal. Surfaces must be clean and profiled or textured. New concrete must be a minimum of 28 days old. All dirt, oil, debris, wax, grease or dust must be removed. Prepare the surface mechanically using a scarifier, sandblast, shot blast, bush hammer or other equipment that will give the surface profile needed for the application. A roughened surface that exposes the aggregate and/or pores of the substrate is imperative for good adhesion.

10. CLEAN UP

Clean tools and equipment with Mighty Wipes by Barricade, a biodegradable formula, that removes and neutralizes the epoxy. Do not allow epoxy to harden on equipment as cured material can only be removed mechanically.

11. SAFETY

Please refer to the SDS for BARRICADE™ Concrete Repair Crack Prep Surface Paste published on our Website, www.barricadesubfloor.com or call Barricade for more information at 1-855-872-3996. This TDS sheet is not intended to list all Safety and Health Requirements necessary for the installation of these products. All Health and Safety Requirements required by OSHA shall be followed.

12. WARRANTY

Barricade warrants to the Buyer that this product is in good quality and conforms to the manufacturer's specifications in force on the date of manufacturer when used in accordance with the Installation Instructions and when stored as directed in the technical literature.

Manufacturer cannot warrant or guarantee any particular method of use, performance or application under any particular condition and Buyer is responsible for determining the suitability of intended purpose and assumes all risks therein. Barricade shall not be liable for any injury, loss, cost of labor or consequential damages either directly, indirectly or incidentally, arising out of the use or misuse of any product sold by Barricade or another distributor. If the product is proven to be in non-conformance, the Buyers sole remedy shall be a refund of the purchase price or replacement of product.